

# US150

## THERMAL TRANSFER RIBBON

## RIBBON SPECIFICATION SHEET WAX/RESIN FLAT-HEAD

US150 is our ultra-premium flat head wax/resin ribbon, designed to provide a high resolution image on to a wide variety of label stocks. It has an excellent smear, scratch resistance and a good chemical resistance.

### RIBBON SPECIFICATIONS

#### ● RIBBON

GRADE : WAX/RESIN, FLAT-HEAD  
COLOUR : BLACK  
THICKNESS : 10.0±0.3 µm  
Anti-static formulation ink

BASE FILM : POLYESTER (4.5±0.3 µm)  
BACK COAT : SILICONE BASED  
INK MELTING POINT : 75 °C

#### ● STORAGE AND USE

STORAGE : 0-40 °C (32-104 °F), 20-80 %RH  
USE : 5-35 °C (41-95 °F), 20-80 %RH

#### ● RECOMMENDED LABEL STOCK

Coated paper, Glossy paper, Synthetic paper  
PET

#### ● CERTIFICATIONS

HEAVY METALS : 2011/65/EU, (EU)2015/863  
(RoHS, RoHS2.0)  
REACH : SVHC free  
HALOGEN-FREE : IEC 61249-2-21  
ISEGA CERTIFIED : Regulation (EC) no.1935/2004  
FDA  
BPA

\*Above documents are available upon request.


#### ● APPLICATION



BARCODE

### RIBBON PERFORMANCE

IMAGE DENSITY (KONICA MINOLTA FD-5)




SCRATCH /SMUDGE RESISTANCE (ANSI)



Pressure: 1.96x10<sup>4</sup> Pa

Stroke Cycle: 500 cycles with corrugated paper

PRINT SPEED (inch/sec)



UV RESISTANCE (%)



168 hours exposed on UV test machine.

TRANSFER SENSITIVITY



SOLVENT RESISTANCE



\* The numerical value indicated on this sheet is catalog value, and is not guarantee value.

\* The information shown above is tentative and subject to change without notice.



• Stoutenburgerweg 15 -B • 3784 VD • Terschuur • Tel. 0342-728728 •  
• KvK: 65869281 • BTW: 8562.96.065.B.01 • NL 54 INGB 00073 62 1 24 •



ISO 9001  
IQA-1784